

## Trimethylol Propane Triglycidyl Ether

Synonyms: TMPEG、TPEG

Cas No: 30499-70-8

MF: C<sub>15</sub>H<sub>26</sub>O<sub>6</sub>

MW: 302



### ■ Specification:

Item	Standard
Appearance	Colorless Transparent Liquid
Color(APHA)	≤ 40
Viscosity mPa.s (25°C)	100-200
Epoxy Value Eq/100g	0.69-0.74
Epoxy Equivalent Weight g/eq	135-145
Hydrolyzable Chloride %	≤ 0.30
Inorganic Chlorine mg/kg	≤ 20
Moisture Content %	≤ 0.1
Packing	20kg/barrel or 200 kg/barrel, or 1000kgs/IBC container

### ■ Product Application:

TMPEG to be used as epoxy resin reactive diluent, modified treating agent of polyester and other resin, anti-crinkle treating agent of fiber, epoxy embedding material, casting material/adhesive, floor material, solventless coating, adhesives.

#### ZXCHEM

9F, New Caohejing Building, No. 509 Caobao Rd, Shanghai China

Tel 86-21-54265599

Fax 86-21-64821868

Email: sales@zxchem.com.cn

Website: www.zxchem.com